

SPECIFICATION

电池规格书

| | |
|---------------------------|---|
| Customer Name 客户名称 | |
| Model Name 产品名称 | XTAR 26650 5200 保护锂电池(大平凸头) |
| Product number 产品料号 | XBL12003 |
| Description 规格描述 | XTAR26650/3.6V5200mAh/26.5±0.3*69.3±0.5mm/ 持续 10A/国产 |
| Document Revision 文件版本 | A0 |
| Effective Date 生效日期 | 2020/10/27 |

| | | |
|----------------------|------------------|-------------------|
| Made By 制定 陈土庆 | Checked By 审核 | Approved By 批注 |
|----------------------|------------------|-------------------|

| | |
|-------------------------------|-----------------------|
| Customer Confirmation 客户确认 | Company Name 公司名称: |
| | Signature 签名: |

Address: 5th floor, 77 Xinhe Road, Baolai Industrial Zone, Shangmu Community, Pinghu Street, Longgang District, Shenzhen

地址: 深圳市龙岗区平湖街道上木古社区宝来工业区新河路 77 号 5 楼

Content

目录

| | |
|--|----|
| 1、Scope 适用范围..... | 4 |
| 2、Revise 修订..... | 4 |
| 3 Test conditions 电池测试条件..... | 4 |
| 3.1 Standard test conditions 标准测试条件..... | 4 |
| 4、Battery overview 电池概述..... | 5 |
| 4.1 Category 类别..... | 5 |
| 4.2 Product Composition (Model) 产品组成 (型号) | 5 |
| 5、Electrical performance of batteries 电池电性能..... | 5 |
| 5.1 Testing conditions 测试条件..... | 5 |
| 5.2 Electrical performance of batteries 电池电性能..... | 5 |
| 6、Battery reliability test 电池可靠性测试..... | 7 |
| 6.1 Testing conditions 测试条件..... | 7 |
| 6.2 Battery reliability test 电池可靠性试验..... | 7 |
| 7、Battery Safety Testing 电池安全性测试..... | 10 |
| 8、Component drawing 组件图纸..... | 11 |
| 8.1 Assembly Dimension Diagram(mm) | 11 |
| 装配尺寸图 (单位 mm)..... | 11 |
| 8.2 Packaging method 包装方式..... | 11 |
| 9、Main parameters of battery protection panel 电池保护板主要参数..... | 12 |
| 9.1 Testing conditions 测试条件..... | 12 |
| 9.2 Main parameters of protective plate 保护板(IC)主要参数..... | 12 |
| 10、Battery precautions 电池注意事项..... | 13 |
| 11、Other considerations 其他注意事项..... | 14 |

1、Scope 适用范围

It is only suitable for batteries produced by Shenzhen XTAR Electronics Co., Ltd., including lithium ion batteries and protective components.

仅适用于深圳爱克斯达电子有限公司生产的电池，包括锂离子电芯和保护组件。

2、Revise 修订

If the raw materials, production process, production system or battery use environment and requirements change, the proposed change party shall notify the other party in writing of the change information and obtain the consent of both suppliers and buyers before revising it.

如果原材料、生产过程、生产系统或电池使用环境及要求发生改变，提出更改方须将改变的信息以书面形式通知对方取得供需双方同意后再行修订。

3 Test conditions 电池测试条件

The specifications and test methods of rechargeable lithium ion secondary batteries produced by Shenzhen XTAR Electronics Co., Ltd. are standardized to avoid errors caused by different test conditions and methods.

对深圳市爱克斯达电子有限公司生产的可充电锂离子二次电池产品的规格、测试方法进行规范，避免因测试条件、方法的不同引起误差。

3.1 Standard test conditions 标准测试条件

All tests described in this specification are carried out in the following temperature and humidity ranges: 20±5 C and 65 ±20% relative humidity. If the test results are not affected by the temperature and humidity environment, these tests can be carried out in the following temperature and humidity ranges: temperature 15 ~30 C, relative humidity 25%~85%.

本规格书所陈述的所有测试均是在以下温湿度范围进行：20±5℃，相对湿度 65±20%。如果测试结果不受温湿度环境影响时，这些测试可以在以下温湿度范围进行：温度15℃ ~ 30℃，相对湿度 25% ~ 85%。

4、Battery overview 电池概述

4.1 Category 类别

Rechargeable lithium-ion batteries.
可充电锂离子电池。

4.2 Product Composition (Model) 产品组成 (型号)

| Assembly 组件 | Manufacturer 厂商 | Specification type 规格型号 | Number 数量 |
|----------------|--------------------|----------------------------|--------------|
| 电芯 | | INR26650 | 1 |
| PCM | 爱克斯达 | FSJ-1S-R26 | 1 |

5、Electrical performance of batteries 电池电性能

5.1 Testing conditions 测试条件

Atmospheric pressure: 86-106 Kpa
大气压: 86~106Kpa

5.2 Electrical performance of batteries 电池电性能

| NO. 序号 | Items 项目 | Standards 标准 |
|-----------|---------------------------|-----------------|
| 1 | Nominal Voltage 标称电压 | 3.6V |
| 2 | Shipment capacity 出货容量 | SOC60% |
| 3 | Nominal capacity 标称容量 | 5000mAh |
| 4 | Mini capacity 最小容量 | 4800mAh |
| 5 | Discharge Cut-off Voltage | 2.75V |

| | | |
|----|---|--|
| | 放电截止电压 | |
| | Internal resistance 内阻 | $\leq 45m\Omega$ |
| 6 | Charging mode 充电方式 | 恒流恒压充电 |
| 7 | Standard charge 标准充电 | Limit voltage 4.2V, constant current 1000mA, cut-off current 100mA (0.02C), ambient temperature 25°C 限压4.2V, 恒流1000mA, 截止电流100mA(0.02C), 环境温度25°C |
| 8 | Fast charging 快速充电 | Limit voltage 4.2V, constant current 2500mA (0.5C), cut-off current 50mA (0.01C), ambient temperature 25°C 限压4.2V, 恒流2500mA (0.5C), 截止电流50mA(0.01C), 环境温度25°C |
| 9 | Standard charging voltage 标准充电电压 | $4.2 \pm 0.03V$ |
| 10 | Standard charging current 标准充电电流 | 1000mA |
| 11 | Max charging current 最大充电电流 | 2500mA |
| 12 | Standard discharge 标准放电 | Pressure Limit 2.75V(Constant Current 5000mA, Ambient Temperature 25 C) 限压2.75V (恒流5000mA, 环境温度25°C) |
| 13 | Overcharge Voltage Protection 过充电压保护 | $4.28 \pm 0.25V$ |
| 14 | Overcharge recovery voltage 过充恢复电压 | $4.08 \pm 0.05V$ |
| 15 | Over-discharge protection voltage 过放保护电压 | $2.8 \pm 0.25V$ |
| 16 | Over-discharge recovery voltage 过放恢复电压 | $2.8 \pm 0.25V$ |
| 17 | Discharge Overcurrent Protection 放电过流保护 | 10~13A |
| 18 | Weight (g) 重量(g) | 97g |

| | | |
|----|-----------------------------|--|
| 19 | Dimension (mm) 尺寸 (mm) | $\phi (26.5 \pm 0.3) * L (69.3 \pm 0.5)$ |
| 20 | Working temperature 工作温度 | Charging: 0~+45°C Discharge : -20~+60°C 充电: 0~45°C 放电: -20~+60°C |
| 21 | Storage temperature 贮存温度 | 1 year: -20 ~ +25°C 3 months: -20 ~ +40°C 1 month: -20 ~ +50°C 1 年: -20 ~ +25°C 3 个月: -20 ~ +40°C 1 个月: -20 ~ +50°C |
| 22 | Storage humidity 贮存湿度 | 65±20% |
| 23 | Transport voltage 运输电压 | 3.6~3.9V |

6、Battery reliability test 电池可靠性测试

6.1 Testing conditions 测试条件

Atmospheric pressure: 86~106 KPa
大气压力: 86~106KPa

6.2 Battery reliability test 电池可靠性试验

| NO. 序号 | Items 项目 | Test methods and conditions 测试方法及条件 | Standards 标准 |
|-----------|---------------------------|---|--|
| 1 | Free fall testing 自由跌落 | The charged battery PACK is dropped from a height of 1.0m to a hardwood board of 18mm thickness placed on the cement floor, once at both ends of the positive and negative electrodes of the core and once at the cylindrical surface. 将充满电的电池PACK 从1.0m 的高度上跌落到放置在水泥地面上的18mm 厚的硬木板上, 电芯正负极两端各一次, 圆柱面一次。 | Batteries do not leak, fire or explode. 电池不漏液, 不起火, 不爆炸 |

| | | | |
|---|---|---|--|
| 2 | Shock testing 震动 | Fixed the charged battery on the vibration platform, and vibrated for 90 minutes in three directions of X, Y and Z according to the vibration frequency of 10-55 HZ, displacement single amplitude of 0.8 mm. 将充满电的电池固定在振动平台上, 按振动频率10-55HZ, 位移单振幅: 0.8mm, 以X, Y, Z三个方向分别振动90min。 | Batteries do not leak, fire or explode. 电池不漏液, 不起火, 不爆炸 |
| 3 | High temperature performance 高温性能 | The standard charged cores were placed in the thermostat for 2 hours at 55±2 °C, then discharged with 1C current to the termination voltage. 在55±2 °C条件下, 将标准充电后的电芯放入恒温箱中2h 后, 再以1C 电流放电至终止电压。 | 85% of the initial capacity can be released. 可放出初始容量85% |
| 4 | Low temperature performance 低温性能 | The standard charged cores were placed in the thermostat for 2 hours at -10 ±2°C, and then discharged with 0.2C current to the termination voltage. 在-10±2°C条件下, 将标准充电后的电芯放入恒温箱中2h 后, 再以0.2C 电流放电至终止电压。 | 65% of the initial capacity can be released. 可放出初始容量65% |
| 5 | Storage at high and low temperatures 高低温贮存 | After the battery is fully charged, the battery is placed in a high temperature box of 55±2 °C for 2 hours at constant temperature, then placed at ambient temperature of 20 ±5 °C for 4 hours in a low emperature box of -20 ±2 °C and then placed at ambient temperature of 20 ±5 °C for 4 hours. The battery is continued to circulate 10 times according to high temperature - normal temperature - low temperature - normal temperature - high temperature - high 电池充满电后, 将电池放入55±2 °C的高温箱中恒温2小时, 再在环境温度20 ±5 °C下放置4小时, 然后放入-20 ±2 °C的低温箱中恒温2小时, 再在环境温度20±5°C下放置4小时, 继续按高温— | There is no deformation or explosion in the appearance of the battery, and the battery is normally charged and discharged. 电池外观无变形或爆裂现象, 电池充放电正常。 |

| | | | |
|---|---|---|--|
| | | 常温— 低温— 常温— 高温循环10次。 | |
| 6 | Humidity and heat test 湿度和热度测试 | The standard charged cores were placed in boxes with temperature of $40 \pm 2^{\circ}\text{C}$ and relative humidity of 90%-95%, and kept for 48 hours. 将标准充电后的电芯放入温度为 $40 \pm 2^{\circ}\text{C}$ ，相对湿度90%~95%的箱子中，保持48h。 | No explosion, no fire 无爆炸、无起火 |
| 7 | Cycle life 循环寿命 | Constant current 0.5C charge to 4.2V, then constant voltage charge to current declines to 0.01C, rest 10min, constant current 1C discharge to 2.75V, rest 10min. Repeat above steps till continuously discharging capacity Higher than 80% of the Initial Capacities of the Cells 先用0.5 C恒流充电至4.2V，再恒压4.2V充电直至充电电流 $\leq 150\text{mA}$ ，搁置30分钟，再用0.5C电流放电至2.75V；又搁置30分钟，重复以上步骤，直到放电容量是初始容量的70% | ≥ 500 times (次) |
| 8 | Thermal shock 热冲击 | Put the cells in the oven. The temperature of the oven is to be raised at $5 \pm 2^{\circ}\text{C}$ per minute to a temperature of $130 \pm 2^{\circ}\text{C}$ and remains 30 minutes. 将电池放进烘箱内，以 $5 \pm 2^{\circ}\text{C}/\text{min}$ 速度升高烘箱内温度至 $130 \pm 2^{\circ}\text{C}$ 后，恒温30min. | No explosion, no fire 无爆炸、无起火 |
| 9 | Capability of keeping electricity 荷电保持能力 | After full charging, the battery was stored for 28 days at ambient temperature of $20 \pm 5^{\circ}\text{C}$, and then discharged at constant current of 0.5C until the battery could not be discharged. 完全充电后在环境温度为 $20 \pm 5^{\circ}\text{C}$ 的条件下，储存28天，然后进行0.5C恒流放电至电池不能放电止。 | Discharge capacity ($\geq 85\%$) 放电容量 $\geq 85\%$ |


7、Battery Safety Testing 电池安全性测试

| NO. 序号 | Items 项目 | Test methods and conditions 测试方法及条件 | Standards 标准 |
|-----------|--|--|----------------------------------|
| 1 | Overcharging test 过充电试验 | After standard charge, cell is to be charged at 1C1 current until the voltage achieves 6.3V or the total charging time achieves 60 min. Observing the cell temperature while testing, the peak temperature will be less than 150°C. Keep 1h. 电芯按标准充电制式充电结束后，以1C1恒流恒压充电，至电池电压达到1.5倍的上限截止电压或充电时间达到60 min，其中一个条件优先达到即停止试验。试验过程中监视电池温度变化，最高温度应小于150 °C。观察1h | No explosion, no fire 无爆炸、无起火 |
| 2 | Over-discharge protection test 过放保护试验 | After standard charge, cell is to be discharged at 1C1 current for 90min; Keep1h. 电芯按标准充电制式充电结束后，以1C恒流放电90min。观察1h。 | No explosion, no fire 无爆炸、无起火 |
| 3 | Short circuit test 短路试验 | After standard charge, cell is to be short-circuited by connecting the positive and negative terminals under the temperature of 25°C ±2°C with a maximum resistance load of 5mΩ for 10min. Observing the cell temperature while testing, the peak temperature will be less than 150°C. Keep 1h. 电芯按标准充电制式充电结束后，电池放置在25±2 °C的环境中，然后将单 体电池经外部短路10 min，外部线路电阻应小于5 mΩ；试验过程中监视电池温度变化，最高温度应小于150 °C。观察1h。 | No explosion, no fire 无爆炸、无起火 |

8、Component drawing 组件图纸

8.1 Assembly Dimension Diagram(mm)

装配尺寸图 (单位 mm)



8.2 Packaging method 包装方式

(待定)

9、Main parameters of battery protection panel 电池保护板主要参数

9.1 Testing conditions 测试条件

Temperature: $20 \pm 5^{\circ}\text{C}$

温度: $20 \pm 5^{\circ}\text{C}$

Relative humidity: 45~75%

相对湿度: 45~75%

Atmospheric pressure: 86~106KPa

大气压: 86~106KPa

9.2 Main parameters of protective plate 保护板(IC)主要参数

| Parameter 参数 | Symbol 符号 | Testing conditions 测试条件 | MIN. 最小值 | TYP 典型值 | MAX. 最大值 | Unit 单位 |
|--|--------------|----------------------------|-------------|------------|-------------|------------|
| Supply Cu 工作电压 | VDD | -- | -- | 3.7 | -- | V |
| Working current 工作电流 | IDD | VDD=3.9V | -- | 3.0 | 6.0 | uA |
| Quiescent current 静态电流 | | | | | 0.1 | uA |
| Overcharge Detection Voltage 过充电检测电压 | VOCP | -- | 4.25 | 4.28 | 4.31 | V |
| Overcharge Release Voltage 过充电释放电压 | VOCR | -- | 4.03 | 4.08 | 4.13 | V |
| Over discharge detection voltage 过放电检测电压 | VODP | -- | 2.75 | 2.8 | 2.85 | V |
| Over discharge Release Voltage 过放电释放电压 | VODR | -- | 2.75 | 2.8 | 2.85 | V |

| | | | | | | |
|--|-----|-----|-------|------|-------|----|
| Over current detection 过电流检测 | VI | --- | 0.085 | 0.1 | 0.115 | V |
| Overcharge Detection Delay Time 过充检测延迟时间 | TOC | | | 1200 | | ms |
| Delay time of over-radiation detection 过放检测延迟时间 | TOD | | | 144 | | ms |
| Over current detection delay time 过电流检测延迟时间 | TOI | | | 9 | | ms |
| Short circuit protection delay time 短路保护延迟时间 | | | | 320 | | us |
| Continuous on-load current 持续带载电流 | --- | --- | 9 | | | A |

10、Battery precautions 电池注意事项

1. Disassembly is prohibited 禁止拆卸

1) Do not disassemble the battery 不要拆卸电池

Removal of batteries can lead to short circuit inside batteries, which can cause fire, explosion, harmful gases or other problems. Problem.

拆卸电池会发生电池内部短路，会引起起火、爆炸、有害气体或者其它问题。

2) Electrolyte is harmful 电解液是有害的

In case the electrolyte touches the skin and enters the eyes, it should be washed with clean water immediately and the doctor should be consulted.

万一电解液沾到皮肤、进入眼睛，应立即用清水冲洗以及求助医生。

2. Don't dump batteries in the fire 不要把电池倾倒在火中

Do not burn batteries or they will explode. This is dangerous and must be prohibited.

不要焚毁电池，否则会致电池爆炸，这个很危险，必须禁止。

3. No immersion of batteries 禁止浸泡电池

Please do not immerse the battery in liquids, such as clear water, sea water, and non-alcoholic drinks, juices, coffee or other beverages.

请不要把电池浸泡在液体中，像清水、海水，及非酒精饮料、果汁、咖啡 或者其他饮料。

4. Replacement of batteries 更换电池

Replacement of batteries should be completed by battery manufacturers or equipment suppliers. Users should not replace batteries by themselves.

更换电池应由电池生产商或设备供应商完成，用户不要自行更换。

5. Prohibit the use of damaged batteries 禁止使用损坏的电池

Batteries may be damaged by collision during shipment. If abnormal batteries are found, such as damaged packaging, Batteries are wrapped and deformed, smells of electrolyte, leaks are found, etc. Don't use these batteries anymore. electric If the battery has the odor of electrolyte or leaks, the battery should be kept away from the source of fire to avoid fire and explosion.

电池可能在出货途中碰撞而受损。如果发现电池有异常，例如包装损坏、电池包裹变形，有电解液的味道、发现漏液等等，不要再使用这些电池。电池如果有电解液的味道或者出现漏液，电池放置应该远离火源避免起火及爆炸。

11、Other considerations 其他注意事项

- ★ Do not put batteries in heaters, washing machines or high-pressure containers
- ★ Do not charge the battery with an unspecified or unsafe charger.
- ★ If the battery is found to be hot, odorous, discolored, deformed or other abnormal during charging or storage, it should be discontinued.
- ★ Put the battery out of reach of the child to avoid swallowing it.
- ★ When children use batteries, the guardian should explain the operation method in detail.
- ★ Before using batteries, you should read the operation guide in detail and have a deep understanding of the matters needing attention in use.
- ★ Batteries should be charged, used and stored away from static electricity.
- ★ Do not use or leave behind batteries in cars near the source of fire or at temperatures over 60 degrees. Do not charge or discharge in these environments.
- ★ Do not put batteries in handbags with metal items such as necklaces, hairpins, coins or screws, or store batteries with the above items.
- ★ It is forbidden to store lithium batteries in damp places or expose them to

moisture, rain and water.

- ★ In use, attention should be paid to the positive and negative poles of the battery.
- ★ Do not use batteries with severe deformation.
- ★ 不要把电池放在加热器皿、洗衣机或高压容器中。
- ★ 不要使用非指定的和没有安全认证的充电器给电池充电。
- ★ 在使用充电或储存期间如发现电池有变热、散发气味、变色、变形或其它反常之处应停止使用。
- ★ 把电池放到小孩够不到的地方以免吞服。
- ★ 儿童使用电池时，监护人应详细解释操作方法。
- ★ 在使用电池之前，应仔细阅读操作指南并对使用中的注意事项有足够深刻的理解。
- ★ 电池应在远离静电的场所进行充电、使用和储存。
- ★ 不要在火源附近或温度超过60度的轿车中使用或遗留电池，也不要这些环境中进行充放电。
- ★ 不要把电池同项链发夹硬币或螺钉等金属品一起放在手提包中，也不要把电池同上述物品一起储存。
- ★ 禁止将锂电池粒储存在潮湿的地方或者暴露在水汽、雨水和水打湿的地方。
- ★ 在使用时应注意电池的正、负极不要反装。
- ★ 不要使用带有严重变形的电池。